

QUALITY

RMP rubber molded bumpers are made in the USA from 100% cured rubber. They are made for durability and a clean, attractive look.

PROTECTION

Chemical-Resistant Hi-Impact compact design will not warp, rust, rot or harden. Long lasting protection year-round for all-weather applications.

3RD PARTY TESTED

Testing done by: ARDL (Akron Rubber Development Laboratory, Inc.) ARDL is an A2LA ISO 17025 Accredited Testing Laboratory. Certificate # 255.01 & 255.02 ISO 9001:2008 Registered.

MANUFACTURER Roll-Tech Molding Products, LLC 866-431-4515 www.roll-tech.net

RMP Rubber Bumper BUMPR-TB20



Figure 1: RMP BUMPR-TB20 Rubber Bumper

TEST QUALIFICATIONS

- Tensile Strength ASTM D2240-05
- Durometer ASTM D412
- Compression Set ASTM D395-16
- Rebound ASTM D2632-15
- Compressive Deflection ASTM D695-15

ASTM 1170 changed to ASTM F104 in 1962 & no longer supports compressibility & recovery standards.



INSTALLATION

- Pre-drilled, countersunk mounting holes for easy installation.
- 5/8" anchor bolts are mounted through pre-drilled holes.
- Perfect protection for trailers, trucks and wall defense.
- Provides maintenance free in-plant wall protection from forklifts and other material handling vehicles.






Figure 2: RMP BUMPR-TB20 2-D Drawings







TECHNICAL SPECS

Bolt Holes ID: 5/8" Width: 3-1/2" Length: 5-7/8" Height: 3-9/16" Weight: 2.5 Lbs

MANUFACTURING SOLUTIONS

Roll-Tech is a privately held company located in Hickory, NC.

We continue to pioneer the materials industry through the innovation of new products for 20 years & counting.

Our rubber compression molding technology was developed in Europe & was brought to the USA. Now, that technology is used to design, test, & manufacture a diverse line of molded products. A Roll-Tech product is durable, supports heavy loads, sustainable & MADE IN AMERICA.

INFO

For more information on our products or services please visit us on the web at: www.roll-tech.net

Product Features and Test Results




Figure 3: RMP BUMPR-TB20 2-D (Top View)



COMPRESSION SET - 18%

 Material shows stronger elastic network than other bumpers on the market.

BAYSHORE REBOUND - 35%

• Material shows similar rebound to other bumpers on the market.

COMPRESSIVE DEFLECTION (LOAD TO BREAK) - 112,300 lbf

 Material shows similar compressive deflection to other bumpers on the market.


RMP Bumpers Are An Excellent Inexpensive Alternative To Market Materials They Are Field Tested & Made Ready To Use.

TENSILE STRENGTH TO BREAK – 470 psi

 Similar tensile strength to other bumpers on the market.

HARDNESS – 71 ShoreA

Similar hardness to other bumpers on the market.






Figure 4: RMP BUMPR-TB20 2-D (Side View)



---•

243 Performance Dr. SE Hickory, NC 28602 Phone 866.431.4515 Fax 828.431.4515